



## Technical Data Sheet

### **XIAMETER™ OFX-0531 Fluid**

Amino methoxy-functional polydimethylsiloxane

#### **Features & Benefits**

- Excellent detergent resistance
- Durable protection
- Good gloss
- Easy rub out
- Color enhancement
- Premium softener for leather treatments
- Improves abrasion resistance
- Improves water repellency
- Improves surface properties

#### **Composition**

- Solvent solution of an amino-functional siloxane

#### **Applications**

- As an ingredient in detergent-resistant auto polishes and cleaners.
- Imparting durable silicone characteristics into various top coat formulations.
- Minimizing or eliminating problems of silicone transfer or oiling typical of additions of low molecular weight silicones.

#### **Typical Properties**

Specification Writers: These values are not intended for use in preparing specifications.

CTM <sup>1</sup>	Property	Unit	Result
0176	Appearance		Clear, colorless, slightly hazy liquid
0208	Active ingredient	% w/w	50
	Solvents		Aliphatic petroleum distillates and isopropyl alcohol
0004	Viscosity at 25°C	cSt	100–200
0002	Refractive index		1.410
0001	Specific gravity at 25°C		0.865
0021A	Flash point, closed cup	°C	13

1. CTM: Corporate Test Method; copies of CTMs are available on request.

## Description – Auto/Home Care

Some formulations benefit from the use of XIAMETER™ OFX-0531 Fluid and XIAMETER™ OFX-0536 Fluid, while others make use of XIAMETER OFX 0531 Fluid with XIAMETER™ PMX-200 Silicone Fluid. Chemically, XIAMETER OFX-0531 Fluid is a double functional polydimethyl-siloxane. The highly polar nature of the amino-functional groups and the ability of the silicon-functional methoxy groups to cure cause the polish film to deposit and adhere strongly to automobile finishes, chrome and aluminum surfaces.

### Solubility

XIAMETER OFX-0531 Fluid is soluble in many common organic solvents including aliphatic and aromatic hydrocarbon solvents, isobutane and lower alcohols (absolute). The fluid is not soluble in water and hydrolyses in the presence of water. Properly formulated polish emulsions, however, are very stable and do not lose performance benefits upon ageing. The fluid may also be made more water accepting with acetic acid or other organic acids.

### Detergent Resistance

XIAMETER OFX-0531 Fluid resists removal by common car wash detergents. Solvent systems were evaluated in side by side panel tests. Polish was applied, rubbed out and dried overnight. An area of panel was then scrubbed for 30 seconds with a concentrated liquid detergent and washed and unwashed sections were evaluated for gloss. Blends of the fluids gave intermediate detergent resistance (Table 1). The best formulations from this first test were then further evaluated on automobiles which were given a thorough commercial wash each week. Results of this test are given in Table 2. The best formulation, six parts XIAMETER OFX-0531 Fluid and one part XIAMETER OFX-0536 Fluid, had detergent resistance equal to XIAMETER OFX-0536 Fluid alone.

### Polishing Properties

Polish formulas were evaluated on laboratory panels and on automobiles for ease, depth of gloss and detergent resistance. A blend of six parts XIAMETER OFX-0531 Fluid and one part XIAMETER OFX-0536 Fluid was excellent in every case, except for a slight compromise in detergent resistance. Other results are given in Table 3.

### Typical Formulation

XIAMETER OFX-0531 Fluid can be used, depending on desired performance properties, or can be blended to optimize certain properties. It is excellent for formulating liquid, rinse or paste polishes. Polishes formulated with these fluids develop water repellency almost immediately after application, and good detergent resistance develops about three to four hours after application. Optimum detergent resistance develops after about 24 hours.

**Table 1: Detergent Resistance, Panel Test**

Silicone base in formula		After detergent scrubbing
XIAMETER OFX-0531 Fluid		Slight removal of film
XIAMETER OFX-0536 Fluid		No removal of film
XIAMETER OFX-0531 Fluid, six parts	}Blend	Very slight removal of film
XIAMETER OFX-0536 Fluid, one part		
XIAMETER OFX-0536 Fluid, nine parts	}Blend	Film removed
XIAMETER PMX-200 Silicone Fluid, 30,000 mm <sup>2</sup> s <sup>a1</sup> , one part		
XIAMETER PMX-200 Silicone Fluid, 1000 mm <sup>2</sup> s <sup>a1</sup>		Some removal of film

UNRESTRICTED – May be shared with anyone

©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

XIAMETER™ OFX-0531 Fluid

© 2017 The Dow Chemical Company. All rights reserved.

**Table 2: Detergent Resistance, Auto Test**

Silicone base in formula		Car wash cycles, polish remains
XIAMETER OFX-0531 Fluid		7 to 12
XIAMETER OFX-0536 Fluid		10 to 15
XIAMETER OFX-0531 Fluid, six parts	}Blend	10 to 15
XIAMETER OFX-0536 Fluid, one part		
XIAMETER OFX-0536 Fluid, nine parts	}Blend	5 to 10
XIAMETER PMX-200 Silicone Fluid, 30,000 mm <sup>2</sup> s <sup>a1</sup> , one part		
XIAMETER PMX-200 Silicone Fluid, 1000 mm <sup>2</sup> s <sup>a1</sup> (or other dimethylsilicone)		1 to 2

**Table 3: Polish Properties**

Silicone base in formula		Ease of application	Polishing ease
XIAMETER OFX-0531 Fluid		Excellent	Excellent
XIAMETER OFX-0536 Fluid		Good	Good
XIAMETER OFX-0531 Fluid, six parts	}Blend	Excellent	Excellent
XIAMETER OFX-0536 Fluid, one part			
XIAMETER OFX-0536 Fluid, nine parts	}Blend	Excellent	G-Excellent
XIAMETER PMX-200 Silicone Fluid, 30,000 mm <sup>2</sup> s <sup>a1</sup> , one part			
XIAMETER PMX-200 Silicone Fluid		Excellent	Excellent
Silicone base in formula		Depth of gloss	Detergent resistance
XIAMETER OFX-0531 Fluid		Excellent	Good
XIAMETER OFX-0536 Fluid		Fair	Excellent
XIAMETER OFX-0531 Fluid, six parts	}Blend	Excellent	G-Excellent
XIAMETER OFX-0536 Fluid, one part			
XIAMETER OFX-0536 Fluid, nine parts	}Blend	G-Excellent	Fair-Good
XIAMETER PMX-200 Silicone Fluid, 30,000 mm <sup>2</sup> s <sup>a1</sup> , one part			
XIAMETER PMX-200 Silicone Fluid		Excellent	Poor

**Description–  
Textiles**

XIAMETER OFX-0531 Fluid is a solution of amino-functional siloxane in solvent with a combination of alkoxy reactivity and organo-functional amine groups, that adds a new dimension to the properties and possible uses of silicone polymers.

Amine-functional groups facilitate co-reactions with many types of plastics such as polyester, urethanes, acrylics and carboxylic acids, imparting durable silicone characteristics into various top coat formulations.

Since the silicone can be chemically reacted into these various polymer systems the problem of silicone transfer or oiling typical of the additions of low molecular weight silicones can be minimized or eliminated.

## **How To Use– Textiles**

XIAMETER OFX-0531 Fluid is suitable for application by padding, curtain coating or mixing (in closed equipment). The concentration of silicone required to give the desired properties will depend on the fabric or leather construction and the kind of polymer system to be mixed with. Typical doses are between 10 g/1 and 40 g/1 of product for padding and curtain coating application. The dose for mixing with polymer systems, such as urethanes and acrylics, will depend on the degree of finish required. Normally between 0.5 and 1.5% of silicone solids on the dried weight of leather is recommended.

### **Padding/Curtain Coating Application**

1. Pre-dilute the required amount of fluid with an approximately equal weight of solvent (MIBK, aliphatic or aromatic solvents), and add to the mixing tank. Ensure that mixing tank is cold.
2. Top up to final volume with the solvent used to pre-dilute the fluid.

### **Precautions:**

- Start with clean mixing tank, delivery lines, pad box and rollers.
- Always use cold solvent and use in closed equipment.

## **Handling Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT [WWW.CONSUMER.DOW.COM](http://WWW.CONSUMER.DOW.COM), OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## **Usable Life and Storage**

Product should be stored between 0 and 25°C (32 and 77°F) in original, unopened containers.

## **Limitations**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Not intended for human injection. Not intended for food use.

## **Health And Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [www.consumer.dow.com](http://www.consumer.dow.com) or consult your local Dow representative.

<http://www.xiameter.com>

**LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

