



## Technical Data Sheet

### DOWSIL™ Q2-7406 Adhesive

Pressure sensitive adhesive

#### Features & Benefits

- Excellent high-temperature properties
- Adhesion to 288°C (550°F)
- Food-contact capability

#### Composition

- Polydimethylsiloxane gum and resin dispersion; high-viscosity liquid

#### Applications

- General purpose adhesive
- Splicing and plating tapes

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Appearance		Translucent
Diluent		Xylene
Active ingredients	%	55 to 58
Viscosity at 25°C (77°F)	cp	20,000 to 80,000
Specific gravity at 25°C (77°F)		0.98
Flash point, closed cup	°C °F	27 81
<b>Electrical properties of the cured adhesive film<sup>1</sup></b>		
Electric strength <sup>2</sup>	V/mil	653
Dielectric constant		
at 10 <sup>2</sup> Hz		2.93
at 10 <sup>5</sup> Hz		2.87
Dissipation factor		
at 10 <sup>2</sup> Hz		0.004
at 10 <sup>5</sup> Hz		0.001
Volume resistivity	ohm.cm	3.5 x 10 <sup>14</sup>

1. After 96 hours at 23°C (73°F) and 50% relative humidity.
2. Measured with 6.35 mm (1/4 in) electrodes on 2 mil film of adhesive cured on an aluminum panel.

**Description**

DOWSIL™ Q2-7406 Adhesive is a dispersion of polydimethylsiloxane gum and resin. It is diluted with xylene to 55% silicone solids content.

**Food Status**

DOWSIL™ Q2-7406 Adhesive meets FDA requirements for certain food-contact applications. Contact your Dow representative for food-contact information.

**How to Use**

DOWSIL™ Q2-7406 Adhesive can be applied, as supplied, to backing materials by conventional tape coating equipment. It can be further diluted with compatible solvents<sup>1</sup> or blended with other silicone pressure sensitive adhesives before being coated.

**Catalysts**

To achieve a good balance of tack, adhesive strength and cohesive strength over a wide range of operating temperatures, proper cure is essential. One of the factors affecting cure is the catalyst.

Catalysts such as benzoyl peroxide may be used with DOWSIL™ Q2-7406 Adhesive to either accelerate the rate of cure or to allow lower curing temperatures. The use of catalysts also increases the cohesive strength of the adhesive mass and promotes anchorage to the backing material.

Peroxide concentration can be varied from 0.5% to 3.0% (based on adhesive solids), depending upon such factors as backing material, coating equipment, cure cycle and the properties desired. Increasing peroxide concentration in DOWSIL™ Q2-7406 Adhesive will decrease the tack and adhesive strength, but will increase the cohesive strength of the product.

The most consistent results are achieved by using the powdered, 98% benzoyl peroxide. Complete blending of peroxide and adhesive is best obtained by first making a 10% solution of the peroxide in toluene.

**Note:** Solvent dispersions of peroxides should be used within a day or two after mixing, as the peroxide loses its activity quite rapidly in solvent. Thorough dispersion of the adhesive and peroxide during mixing is necessary to achieve uniform results in the finished product.

**Solvent Removal**

To cure DOWSIL™ Q2-7406 Adhesive following its application to the backing material, first remove the solvent. Recommended temperatures for removal range from 66 to 93°C (150 to 200°F). Higher removal temperatures can cause the peroxide to decompose prematurely and crosslink the solvent into the adhesive. This can reduce the properties of the finished tape. The length of time for solvent removal should be sufficient to ensure that no solvent is present in the adhesive when it enters the curing zone.

<sup>1</sup>When using any solvent, always provide adequate ventilation. Follow the solvent manufacturer's safe handling precautions as well as local, state and federal guidelines.

## **How to Use (Cont.)**

### **Curing the Adhesive**

After the solvent is removed, a tacky, uniform film of adhesive is left on the backing. This film's adhesive and cohesive strengths, as well as the tack, can be further developed by a heat cure. The amount of cure depends on a number of factors, including the type of catalyst or equipment and backing material.

A cure of 1 minute at 66°C (150°F) for solvent removal, followed by 2 minutes at 177 to 204°C (350 to 400°F) is used for adhesive that contains benzoyl peroxide.

If equipment and type of backing material permit the use of higher curing temperatures, the cure time may be shortened. Higher cure temperatures develop cohesive strength of the adhesive in less time than at lower temperatures. The ultimate adhesive strength of the fully cured material is essentially the same whether cured at higher or lower temperatures. The only difference is the time required to reach complete cure.

### **Anchorage to Backing**

To achieve maximum anchorage of the adhesive to the backing, a primer may be required. Contact Dow Technical Service for assistance in selecting a primer formulation.

## **Handling Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## **Usable Life and Storage**

When stored at or below 32°C (90°F) in the original unopened containers, this product has a usable life of 24 months from the date of production.

## **Packaging Information**

This product is available in a variety of container sizes. Contact your local Dow Customer Service representative for information about container sizes available in your area.

## **Limitations**

Shipping: DOT Classification: flammable.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## **Health and Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [consumer.dow.com](http://consumer.dow.com) or consult your local Dow representative.

consumer.dow.com

**LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

