



# TPSiV® 4200-70A

## THERMOPLASTIC ELASTOMER

When you combine the strength, toughness, and abrasion resistance of thermoplastic elastomer with the soft silkiness, UV and chemical resistance, and colorability of silicone, you get DuPont™ TPSiV®. Durable, yet both silky and non-tacky (dirt-resistant), TPSiV® delivers exceptional performance and aesthetics.

TPSiV® products incorporate vulcanized silicone in a thermoplastic matrix and can be customized for specific applications and can be recycled and reused in your manufacturing processes. This makes them remarkably versatile and reliable for a wide range of applications.

TPSiV® 4200-70A thermoplastic elastomer is a material with good chemical resistance and excellent abrasion and scratch resistance. It exhibits excellent bonding to polycarbonate, ABS and similar polar substrates. It is a product targeted for soft touch overmoulding on consumer electronics, mobile communication devices, computers and sports & leisure applications.

### Rheological properties

Melt mass-flow rate	27 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	ISO 1133
Melt mass-flow rate, Load	10 kg	ISO 1133
Moulding shrinkage, parallel	2.0 %	ISO 294-4, 2577

### Typical mechanical properties

Stress at 100% elongation	3.9 MPa	ISO 527-1/-2 or ISO 37
Stress at break	14.5 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	>300 %	ISO 527-1/-2 or ISO 37
Flexural Modulus	32.8 MPa	ISO 178
Flexural Strength	2.4 MPa	ISO 178
Shore A hardness, 15s	73	ISO 48-4 / ISO 868
Compression set at 23°C	22 %	ISO 815
Compression set at 70°C, 24h	75 %	ISO 815
Tear strength, normal	48.6 kN/m	ISO 34-1

[1]: Cross direction

### Other properties

Density	1180 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Recommended	yes
Drying Temperature	70 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Melt Temperature Optimum	195 °C
Max. screw tangential speed	0.4 m/s
Mold Temperature Optimum	30 °C
Min. mould temperature	20 °C
Max. mould temperature	40 °C



# TPSiV<sup>®</sup> 4200-70A

## THERMOPLASTIC ELASTOMER

### Extrusion

Drying Temperature	70 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Melt Temperature Range	185 - 205 °C

### Characteristics

Compatibility	Polycarbonate, Styrenics, Acrylic Polymers
---------------	--

### Additional information

Injection molding	TPSiV <sup>®</sup> elastomers products can be manufactured using standard thermoplastic manufacturing processes, including overmolding or co-molding with plastic substrates such as polycarbonate, ABS and nylons. TPSiV <sup>®</sup> elastomers self-adhere to hard plastics to enable unique overmolding options. The extremely silky feel of TPSiV elastomers does not require additional processing or coating steps.
-------------------	--

### DuPont

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.